



(19)

(11) Publication number: **10313128 A**

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **09139440**(51) Intl. Cl.: **H01L 31/04 C30B 33/12 H01L 21/306**(22) Application date: **13.05.97**

(30) Priority:

(43) Date of application publication: **24.11.98**

(84) Designated contracting states:

(71) Applicant: **MATSUSHITA ELECTRIC IND CO LTD**(72) Inventor: **KIM HANMIN
SHIBUYA MUNEHIRO
YOSHIDA TETSUHISA
KITAGAWA MASATOSHI**

(74) Representative:

(54) ANISOTROPICALLY ETCHING METHOD FOR SILICON SUBSTRATE AND MANUFACTURE OF SOLAR CELL

(57) Abstract:

PROBLEM TO BE SOLVED: To deeply form anisotropically etched pits into an Si substrate surface by introducing an etching gas conc. at least either ClF_3 or XeF_2 into a reactor chamber at the atmospheric pressure, and etching the substrate surface at specified temp. with this gas to form anisotropically etched pits thereinto.

SOLUTION: A ClF_3 gas is fed into a reaction chamber 13 at room temp. and atmospheric pressure, at a rate of 0.2 lit./min. with N_2 fed at 2 lit./min. to etch Si 100 and 111 substrate for 2 min. at room temp., thereby forming rectangular and pyramid-like etched pits into the (100)- and (111)-plane substrates. The temp. rise in the structure due to the heat may change the isotropic etching, and hence substrate temp. is suppressed below 130°C . After cooling the substrate, the above steps are repeated to make the anisotropic etching, thus forming a deep irregularities structure. Thus, a substrate having square and pyramid etched pits is formed.

COPYRIGHT: (C)1998,JPO

